



# **AOS Semiconductor**

## **Product Reliability Report**

**AO4818B/AO4818BL, rev A**

**Plastic Encapsulated Device**

**ALPHA & OMEGA Semiconductor, Inc**

**495 Mercury Drive  
Sunnyvale, CA 94085  
U.S.**

**Tel: (408) 830-9742**

**[www.aosmd.com](http://www.aosmd.com)**

**1 Aug, 2007**

This AOS product reliability report summarizes the qualification result for AO4818B. Accelerated environmental tests are performed on a specific sample size, and then followed by electrical test at end point. Review of final electrical test result confirms that AO4818B passes AOS quality and reliability requirements. The released product will be categorized by the process family and be monitored on a quarterly basis for continuously improving the product quality.

## Table of Contents:

- I. Product Description
- II. Package and Die information
- III. Environmental Stress Test Summary and Result
- IV. Reliability Evaluation
- V. Quality Assurance Information

### I. Product Description:

The AO4818B uses advanced trench technology to provide excellent  $R_{DS(ON)}$  and low gate charge. This device is suitable for use as a load switch or in PWM applications. Standard Product AO4818B is Pb-free (meets ROHS & Sony 259 specifications).

Absolute Maximum Ratings $T_A=25^\circ\text{C}$ unless otherwise noted			
Parameter	Symbol	Maximum	Units
Drain-Source Voltage	$V_{DS}$	30	V
Gate-Source Voltage	$V_{GS}$	$\pm 20$	V
Continuous Drain Current	$T_A=25^\circ\text{C}$	8.5	A
	$T_A=70^\circ\text{C}$	6.6	
Pulsed Drain Current	$I_{DM}$	30	
Power Dissipation	$T_A=25^\circ\text{C}$	2	W
	$T_A=70^\circ\text{C}$	1.28	
Avalanche Current	$I_{AR}$	16	
Repetitive avalanche energy 0.3mH	$E_{AR}$	38	
Junction and Storage Temperature Range	$T_J, T_{STG}$	-55 to 150	$^\circ\text{C}$

Thermal Characteristics					
Parameter	Symbol	Typ	Max	Units	
Maximum Junction-to-Ambient	$T \leq 10\text{s}$	$R_{\theta JA}$	48	62.5	$^\circ\text{C/W}$
Maximum Junction-to-Ambient	Steady-State		74	110	$^\circ\text{C/W}$
Maximum Junction-to-Lead	Steady-State	$R_{\theta JL}$	35	40	$^\circ\text{C/W}$

## II. Die / Package Information:

	<b>AO4818B</b>	<b>AO4818BL (Green Compound)</b>
<b>Process</b>	Standard sub-micron	Standard sub-micron
<b>Package Type</b>	Low voltage N channel process	low voltage N channel process
<b>Lead Frame</b>	8 leads SOIC	8 leads SOIC
<b>Die Attach</b>	Copper with Solder spot	Copper with Solder spot
<b>Bond wire</b>	Ag epoxy	Ag epoxy
<b>Mold Material</b>	S: Cu 2mils; G: Au 1.3mil	S: Cu 2mils; G: Au 1.3mil
<b>Filler % (Spherical/Flake)</b>	Epoxy resin with silica filler	Epoxy resin with silica filler
<b>Flammability Rating</b>	90/10	100/0
<b>Backside Metallization</b>	UL-94 V-0	UL-94 V-0
<b>Moisture Level</b>	Ti / Ni / Ag	Ti / Ni / Ag
	Up to Level 1 *	Up to Level 1 *

Note \* based on info provided by assembler and mold compound supplier

## III. Result of Reliability Stress for AO4818B (Standard) & AO4818BL (Green)

Test Item	Test Condition	Time Point	Lot Attribution	Total Sample size	Number of Failures
<b>Solder Reflow Precondition</b>	Standard: 1hr PCT+3 cycle reflow@260°C Green: 168hr 85°C /85%RH +3 cycle reflow@260°C	0hr	Standard: 83 lots Green: 29 lots	17380 pcs	0
<b>HTGB</b>	Temp = 150°C , Vgs=100% of Vgsmax	168 / 500 hrs 1000 hrs	4 lots  (Note A*)	328 pcs  77+5 pcs / lot	0
<b>HTRB</b>	Temp = 150°C , Vds=80% of Vdsmax	168 / 500 hrs 1000 hrs	4 lots  (Note A*)	328 pcs  77+5 pcs / lot	0
<b>HAST</b>	130 +/- 2°C , 85%RH, 33.3 psi, Vgs = 80% of Vgs max	100 hrs	Standard: 81 lots Green: 16 lots  (Note B**)	5335 pcs  50+5 pcs / lot	0
<b>Pressure Pot</b>	121°C , 29.7psi, 100%RH	96 hrs	Standard: 83 lots Green: 20 lots  (Note B**)	5665 pcs  50+5 pcs / lot	0
<b>Temperature Cycle</b>	-65°C to 150°C , air to air	250 / 500 cycles	Standard: 87 lots Green: 29 lots  (Note B**)	6380 pcs  50+5 pcs / lot	0

### III. Result of Reliability Stress for AO4818B (Standard) & AO4818BL (Green) Continues

<b>DPA</b>	Internal Vision Cross-section X-ray	NA	5 5 5	5 5 5	0
<b>CSAM</b>		NA	5	5	0
<b>Bond Integrity</b>	Room Temp 150°C bake 150°C bake	0hr 250hr 500hr	40 40 40	40 wires 40 wires 40 wires	0
<b>Solderability</b>	245°C	5 sec	15	15 leads	0
<b>Die shear</b>	150°C	0hr	10	10	0

**Note A:** The HTGB and HTRB reliability data presents total of available AO4818B and AO4818BL burn-in data up to the published date.

**Note B:** The pressure pot, temperature cycle and HAST reliability data for AO4818B and AO4818BL comes from the AOS generic package qualification data.

### IV. Reliability Evaluation

**FIT rate (per billion): 32**

**MTTF = 3567years**

In general, 500 hrs of HTGB, 150 deg C accelerated stress testing is equivalent to 15 years of lifetime at 55 deg C operating conditions (by applying the Arrhenius equation with an activation energy of 0.7eV and 60% of upper confidence level on the failure rate calculation). AOS reliability group also routinely monitors the product reliability up to 1000 hr at and performs the necessary failure analysis on the units failed for reliability test(s).

The presentation of FIT rate for the individual product reliability is restricted by the actual burn-in sample size of the selected product (AO4818B). Failure Rate Determination is based on JEDEC Standard JESD 85. FIT means one failure per billion hours.

$$\text{Failure Rate} = \text{Chi}^2 \times 10^9 / [2 (N) (H) (Af)] = 1.83 \times 10^9 / [2 (4 \times 164) (168) (258)] = 32$$

$$\text{MTTF} = 10^9 / \text{FIT} = 3.12 \times 10^7 \text{hrs} = 3567\text{years}$$

**Chi<sup>2</sup>** = Chi Squared Distribution, determined by the number of failures and confidence interval

**N** = Total Number of units from HTRB and HTGB tests

**H** = Duration of HTRB/HTGB testing

**Af** = Acceleration Factor from Test to Use Conditions (Ea = 0.7eV and Tuse = 55°C)

Acceleration Factor [**Af**] =  $\text{Exp} [E_a / k (1/T_j u - 1/T_j s)]$

**Acceleration Factor ratio list:**

	55 deg C	70 deg C	85 deg C	100 deg C	115 deg C	130 deg C	150 deg C
<b>Af</b>	<b>258</b>	<b>87</b>	<b>32</b>	<b>13</b>	<b>5.64</b>	<b>2.59</b>	<b>1</b>

**Tj s** = Stressed junction temperature in degree (Kelvin), K = C+273.16

**Tj u** = The use junction temperature in degree (Kelvin), K = C+273.16

**k** = Boltzmann's constant, 8.617164 X 10<sup>-5</sup>eV / K



## V. Quality Assurance Information

Acceptable Quality Level for outgoing inspection: **0.1%** for electrical and visual.

Guaranteed Outgoing Defect Rate: **< 25 ppm**

Quality Sample Plan: conform to **Mil-Std-105D**