

# AOS Semiconductor Product Reliability Report

## A07405/A07405L, rev B

**Plastic Encapsulated Device** 

**ALPHA & OMEGA Semiconductor, Inc** 

495 Mercury Drive Sunnyvale, CA 94085 U.S.

Tel: (408) 830-9742 <u>www.aosmd.com</u>

Feb 15, 2006



This AOS product reliability report summarizes the qualification result for AO7405/AO7405L. Accelerated environmental tests are performed on a specific sample size, and then followed by electrical test at end point. Review of final electrical test result confirms that AO7405/AO7405L passes AOS quality and reliability requirements. The released product will be categorized by the process family and be monitored on a quarterly basis for continuously improving the product quality.

#### **Table of Contents:**

- I. Product Description
- II. Package and Die information
- III. Environmental Stress Test Summary and Result
- IV. Reliability Evaluation
- V. Quality Assurance Information

#### I. Product Description:

The AO7405 uses advanced trench technology to provide excellent  $R_{DS(ON)}$ , low gate charge, and operation with gate voltages as low as 2.5V, in the small SOT363 footprint. It can be used for a wide variety of applications, including load switching, low current inverters and low current DC-DC converters. Standard Product AO7405 is Pb-free (meets ROHS & Sony 259 specifications). AO7405L is a Green Product ordering option. AO7405 and AO7405L are electrically identical.

Absolute Maxim	um Ratings	T <sub>A</sub> =25°C ur	nless otherwise noted		
Parameter		Symbol	Maximum	Units	
Drain-Source Voltage		$V_{DS}$	-30	V	
Gate-Source Voltage		V <sub>GS</sub>	±12	V	
Continuous Drain Current	T <sub>A</sub> =25°C	I <sub>D</sub>	-1.6		
	T <sub>A</sub> =70°C		-1.3		
Pulsed Drain Current		I <sub>DM</sub>	-10	A	
Power Dissipation	T <sub>A</sub> =25°C	P <sub>D</sub>	0.625		
	T <sub>A</sub> =70°C		0.4	W	
Junction and Storage Temperature Range		T <sub>J</sub> , T <sub>STG</sub>	-55 to 150	°C	

Thermal Characteristics							
Parameter		Symbol	Тур	Max	Units		
Maximum Junction- to-Ambient	T ≤ 10s	$R_{\scriptscriptstyle{ hetaJA}}$	160	200			
Maximum Junction- to-Ambient	Steady- State		180	220	°C/W		
Maximum Junction- to-Lead	Steady- State	$R_{ heta JL}$	130	160			



### II. Die / Package Information:

AO7405 AO7405L (Green Compound)

Process Standard sub-micron Standard sub-micron

low voltage P channel process low voltage P channel process

Package TypeSC-70 3LSC-70 3LLead FrameAlloy 42 Ag spotAlloy 42 Ag spotDie AttachSilver epoxySilver epoxyBondwire1.3mils Au wire1.3mils Au wire

Mold Material Epoxy resin with silica filler Epoxy resin with silica filler

Flammability Rating UL-94 V-0 UL-94 V-0

Backside Metallization Ti / Ni / Ag

Moisture Level Up to Level 1\*

UL-94 V-0 UL-94 V-0

Ti / Ni / Ag

Up to Level 1\*

Note \* based on info provided by assembler and mold compound supplier

#### III. Result of Reliability Stress for AO7405 (Standard) & AO7405L (Green)

Test Item	Test Condition	Time Point	Lot Attribution	Total Sample size	Number of Failures
Solder Reflow Precondition	Standard: 1hr PCT+3 cycle reflow@260°c Green: 168hr 85°c/85RH +3 cycle reflow@260°c	0hr	Standard: 4 lots Green: 4 lots	1265 pcs	0
HTGB	Temp = 150°c, Vgs=100% of Vgsmax	168 / 500 hrs	4 lots	328 pcs	0
		1000 hrs	(Note A*)	77+5 pcs / lot	
HTRB	Temp = 150°c, Vds=80% of Vdsmax	168 / 500 hrs	4 lots	328 pcs	0
	1 us=50 /0 01 v usmax	1000 hrs	(Note A*)	77+5 pcs / lot	
HAST	130 +/- 2°c, 85%RH, 33.3 psi, Vgs = 80% of	100 hrs	Standard: 4 lots Green: 4 lots	440 pcs	0
	Vgs max		(Note B**)	50+5 pcs / lot	
Pressure Pot	121°c, 29.7psi, RH=100%	96 hrs	Standard: 4 lots Green: 3 lots	385 pcs	0
			(Note B**)	50+5 pcs / lot	
Temperature Cycle	-65°c to 150°c, air to air, 0.5hr per cycle	250 / 500 cycles	Standard: 4 lots Green: 4 lots	440 pcs	0
Cycle	am to am, erom per cyclo		(Note B**)	50+5 pcs / lot	
DPA	Internal Vision Cross-section	NA	5 5	5 pcs 5 pcs	0
	X-ray		5	5 pcs	
CSAM		NA	5	5 pcs	0



Bond Integrity	Room Temp 150°c bake 150°c bake	0hr 250hr 500hr	40 40 40	40 wires 40 wires 40 wires	0
Solderability	230°c	5 sec	15	15 leads	0
Die shear	150°c	0hr	10	10 pcs	0

**Note A:** The HTGB and HTRB reliability data presents total of available AO7405 and AO7405L burn-in data up to the published date.

**Note B:** The pressure pot, temperature cycle and HAST reliability data for AO7405 and AO7405L comes from the AOS generic package qualification data.

#### IV. Reliability Evaluation

FIT rate (per billion): 11.7 MTTF = 9757 years

In general, 500 hrs of HTGB, 150 deg C accelerated stress testing is equivalent to 15 years of lifetime at 55 deg C operating conditions (by applying the Arrhenius equation with an activation energy of 0.7eV and 60% of upper confidence level on the failure rate calculation). AOS reliability group also routinely monitors the product reliability up to 1000 hr at and performs the necessary failure analysis on the units failed for reliability test(s).

The presentation of FIT rate for the individual product reliability is restricted by the actual burn-in sample size of the selected product (AO7405). Failure Rate Determination is based on JEDEC Standard JESD 85. FIT means one failure per billion hours.

Failure Rate = 
$$\text{Chi}^2 \times 10^9 \text{/} [2 \text{ (N) (H) (Af)}]$$
  
=  $1.83 \times 10^9 \text{/} [2 (2 \times 164) (168) (258) + 2 (164) (500) (258) + 2 (164) (1000) (258)] = 11.7$ 

**MTTF** = 
$$10^9$$
 / FIT =  $8.54 \times 10^7$  hrs =  $9757$  years

Chi² = Chi Squared Distribution, determined by the number of failures and confidence interval

**N** = Total Number of units from HTRB and HTGB tests

**H** = Duration of HTRB/HTGB testing

Af = Acceleration Factor from Test to Use Conditions (Ea = 0.7eV and Tuse = 55°C)

Acceleration Factor [Af] = Exp [Ea / k (1/Tj u - 1/Tj s)]

**Acceleration Factor ratio list:** 

	55 deg C	70 deg C	85 deg C	100 deg C	115 deg C	130 deg C	150 deg C
Af	258	87	32	13	5.64	2.59	1

Tj s = Stressed junction temperature in degree (Kelvin), K = C+273.16

Tj u = The use junction temperature in degree (Kelvin), K = C+273.16

**k** = Boltzmann's constant, 8.617164 X 10<sup>-5</sup>eV / K



V. Quality Assurance Information
Acceptable Quality Level for outgoing inspection: 0.1% for electrical and visual.
Guaranteed Outgoing Defect Rate: < 25 ppm
Quality Sample Plan: conform to Mil-Std-105D