

# ***Alpha & Omega Semiconductor Product Reliability Qualification Report***

**AOCA72114** rev A

**Plastic Encapsulated Device**

**ALPHA & OMEGA Semiconductor, Inc**

**[www.aosmd.com](http://www.aosmd.com)**

This report delineates the product's quality and reliability test outcomes. Specific sample sizes undergo accelerated environmental tests, with corresponding electrical testing before and after each interval. Analysis of the conclusive electrical test results affirms the product's adherence to AOS quality and reliability standards in accordance with JEDEC. Reference to the existing qualification outcomes for similar products is warranted due to structural similarities. The released product will be classified by its process family and undergo regular monitoring to ensure continual enhancements in product quality.

## I. Reliability Stress Test Summary and Results

Test Item	Test Condition	Duration	Lots/SS	Number of Failures	Reference Standard
<b>HTGB</b> <i>High Temperature Gate Bias</i>	150°C Vgs=100% of Vgsmax	1000 hrs	3 * 77	0/231	JESD22-A108
<b>HTRB</b> <i>High Temperature Reverse Bias</i>	150°C Vds=100% of Vdsmax	1000 hrs	3 * 77	0/231	JESD22-A108
<b>PC</b> <i>Precondition</i>	168 hrs, 85°C, 85%RH, 3 cycles reflow @ 260°C <b>(MSL 1)</b>	-	12 * 77	0/924	JESD22-A113 J-STD-020
<b>UHASt*</b> <i>Unbiased Highly Accelerated Stress Test</i>	130°C, 85%RH	96 hrs	3 * 77	0/231	JESD22-A118
<b>AC*</b> <i>Autoclave</i>	121°C, 100%RH, 15psig	96 hrs	3 * 77	0/231	JESD22-A102
<b>TC*</b> <i>Temperature Cycling</i>	-65°C to 150°C, air to air	1000 cycles	3 * 77	0/231	JESD22-A104
<b>IOL*</b> <i>Intermittent Operational Life</i>	$\Delta T_j = 100^\circ\text{C}$ $t_{on} = 2 \text{ minutes}$ $t_{off} = 2 \text{ minutes}$	10000 cycles	3 * 77	0/231	MIL-STD-750 Method 1037
<b>ESD_HBM</b>	Class 2 (2000V~3999V)	-	3 pcs	-	JS-001
<b>ESD_CDM</b>	Class C3 ( $\geq 1000\text{V}$ )	-	3 pcs	-	JS-002

**Notes:**

\* For SMD devices reliability stress tests performed after PC (precondition).

## II. Reliability Evaluation

**FIT rate (per billion): 7.63**

**MTTF = 14960 years**

The presentation of FIT rate for the individual product reliability is restricted by the actual burn-in sample size. Failure Rate Determination is based on JEDEC Standard JESD 85. FIT means one failure per billion hours.

At 60% Confidence Level

**Failure Rate** =  $\text{Chi}^2 \times 10^9 / [2 (N) (H) (Af)] = 7.63$

**MTTF** =  $10^9 / \text{FIT} = 14960$  years

**Chi<sup>2</sup>** = Chi Squared Distribution, determined by the number of failures and confidence interval

**N** = Total Number of units from burn-in tests

**H** = Duration of burn-in testing

**Af** = Acceleration Factor from Test to Use Conditions (Ea = 0.7eV and T<sub>J u</sub> = 55°C)

Acceleration Factor [**Af**] = **Exp** [Ea / k (1/T<sub>J u</sub> - 1/T<sub>J s</sub>)]

### Acceleration Factor ratio list:

	55 deg C	70 deg C	85 deg C	100 deg C	115 deg C	130 deg C	150 deg C
Af	259	87	32	13	5.64	2.59	1

T<sub>J s</sub> = Stressed junction temperature in degree (Kelvin), K = C + 273.16

T<sub>J u</sub> = The use junction temperature in degree (Kelvin), K = C + 273.16

k = Boltzmann's constant, 8.617164 X 10<sup>-5</sup>eV / K