

Alpha & Omega Semiconductor Product Reliability Qualification Report

AOK160A60FDL rev A

Plastic Encapsulated Device

ALPHA & OMEGA Semiconductor, Inc

www.aosmd.com

This report delineates the product's quality and reliability test outcomes. Specific sample sizes undergo accelerated environmental tests, with corresponding electrical testing before and after each interval. Analysis of the conclusive electrical test results affirms the product's adherence to AOS quality and reliability standards in accordance with JEDEC. Reference to the existing qualification outcomes for similar products is warranted due to structural similarities. The released product will be classified by its process family and undergo regular monitoring to ensure continual enhancements in product quality.

I. Reliability Stress Test Summary and Results

| Test Item | Test Condition | Duration | Lots/SS | Number of Failures | Reference Standard |
|--|---|-------------|---------|--------------------|----------------------------|
| HTGB <i>High Temperature Gate Bias</i> | 150°C Vgs=100% of Vgsmax | 1000 hrs | 3 * 77 | 0/231 | JESD22-A108 |
| HTRB <i>High Temperature Reverse Bias</i> | 150°C Vds=100% of Vdsmax | 1000 hrs | 3 * 77 | 0/231 | JESD22-A108 |
| HAST <i>Highly Accelerated Stress Test</i> | 130°C, 85%RH, Vds = 80% of Vdsmax up to 42V | 96 hrs | 3 * 77 | 0/231 | JESD22-A110 |
| H3TRB <i>High Humidity High Temperature Reverse Bias</i> | 85°C, 85%RH, Vds = 80% of Vdsmax up to 100V | 1000 hrs | 3 * 77 | 0/231 | JESD22-A101 |
| AC <i>Autoclave</i> | 121°C, 100%RH, 15psig | 96 hrs | 3 * 77 | 0/231 | JESD22-A102 |
| TC <i>Temperature Cycling</i> | -65°C to 150°C, air to air | 1000 cycles | 3 * 77 | 0/231 | JESD22-A104 |
| IOL <i>Intermittent Operational Life</i> | $\Delta T_j = 100^\circ\text{C}$ $t_{on} = 5$ minutes $t_{off} = 5$ minutes | 6000 cycles | 3 * 77 | 0/231 | MIL-STD-750 Method 1037 |
| ESD_HBM | Class 2 (2000V~3999V) | - | 3 pcs | - | JS-001 |
| ESD_CDM | Class C3 ($\geq 1000\text{V}$) | - | 3 pcs | - | JS-002 |

II. Reliability Evaluation

FIT rate (per billion): 7.63

MTTF = 14960 years

The presentation of FIT rate for the individual product reliability is restricted by the actual burn-in sample size. Failure Rate Determination is based on JEDEC Standard JESD 85. FIT means one failure per billion hours.

At 60% Confidence Level

Failure Rate = $\text{Chi}^2 \times 10^9 / [2 (N) (H) (Af)] = 7.63$

MTTF = $10^9 / \text{FIT} = 14960$ years

Chi² = Chi Squared Distribution, determined by the number of failures and confidence interval

N = Total Number of units from burn-in tests

H = Duration of burn-in testing

Af = Acceleration Factor from Test to Use Conditions ($E_a = 0.7\text{eV}$ and $T_{J u} = 55^\circ\text{C}$)

Acceleration Factor [**Af**] = **Exp** [$E_a / k (1/T_{J u} - 1/T_{J s})$]

Acceleration Factor ratio list:

| | 55 deg C | 70 deg C | 85 deg C | 100 deg C | 115 deg C | 130 deg C | 150 deg C |
|-----------|----------|----------|----------|-----------|-----------|-----------|-----------|
| Af | 259 | 87 | 32 | 13 | 5.64 | 2.59 | 1 |

T_{J s} = Stressed junction temperature in degree (Kelvin), $K = C + 273.16$

T_{J u} = The use junction temperature in degree (Kelvin), $K = C + 273.16$

k = Boltzmann's constant, $8.617164 \times 10^{-5}\text{eV} / \text{K}$