

Alpha & Omega Semiconductor Product Reliability Qualification Report

AOTL66810Q rev A

Plastic Encapsulated Device

ALPHA & OMEGA Semiconductor, Inc

www.aosmd.com



The report summarizes the AOS product reliability qualification results. Accelerated environmental tests are performed on a specific sample size and samples are electrically tested before and after each time point. Review of final electrical test results confirms that the product passes the AOS quality and reliability requirements based on **AEC-Q101** and may reference existing qualification results of similar products, which is justified by the structural similarity of the products. The released product will be categorized by its process family and routinely monitored for continuous improvement of product quality.

I. Reliability Stress Test Summary and Results

Test Item	Test Condition	Time Point	Total Sample Size	Number of Failures	Reference Standard
HTGB	Temp = 175°C Vgs=100% of Vgsmax	1000 hrs	231 pcs	0	JESD22-A108
HTRB	Temp = 175°C Vds=100% of Vdsmax	1000 hrs	231 pcs	0	JESD22-A108
Precondition	168hr, 85°C, 85%RH, 3 cycle reflow @ 260°C (MSL 1)	-	231*5 pcs	0	JESD22-A113 J-STD-020
HAST	130°C, 85%RH, 33.3 psia, Vds = 80% of Vdsmax up to 42V	96 hrs	231 pcs	0	JESD22-A110
нзткв	85°C, 85%RH, Vds = 80% of Vdsmax up to 100V	1000 hrs	231 pcs	0	JESD22-A101
Autoclave	121°C, 100%RH, 29.7psia	96 hrs	231 pcs	0	JESD22-A102
Temperature Cycle	-55°C to 150°C, air to air	1000 cycles	231 pcs	0	JESD22-A104
IOL	$\Delta Tj = 100$ °C $t_{on} = 2$ minutes $t_{off} = 2$ minutes	15000 cycles	231 pcs	0	MIL-STD-750 Method 1037
TCDT	100% CSAM inspection or WBP	-	15 pcs	0	JESD22-A-104
TC+DPA	Decap and inspection with 50x magnification	-	6 pcs	0	AEC-Q101-004
HAST+DPA	Decap and inspection with 50x magnification	-	6 pcs	0	AEC-Q101-004
H3TRB+DPA	Decap and inspection with 50x magnification	-	6 pcs	0	AEC-Q101-004
PD	-	-	30 pcs	0	JESD22-B-100
cs	-	-	15 pcs	0	-
DS	-	-	15 pcs	0	MIL-STD-750-2 Method 2017
RSH	-	-	30 pcs	0	JESD22-A-111 (SMD) or B-106 (PTH)
TR	-	-	10 pcs	0	JESD24-3, 24-4, 24-6 as appropriate



SD	-	-	10 pcs	0	J-STD-002
DI	-	-	5 pcs	0	AEC-Q101-004
PV	Tj= -55°C,25°C,175°C	-	75 pcs	0	datasheet
UIS	-	-	5 pcs	0	AEC-Q101-004
ESDH	Class H3A (4001V~8000V)	-	30 pcs	0	AEC-Q101-001
ESDC	Class C5 (>1000V)	-	30 pcs	0	AEC-Q101-005

II. Reliability Evaluation

FIT rate (per billion): 2.61 MTTF = 43670 years

The presentation of FIT rate for the individual product reliability is restricted by the actual burn-in sample size. Failure Rate Determination is based on JEDEC Standard JESD 85. FIT means one failure per billion hours.

At 60% Confidence Level

Failure Rate = $\text{Chi}^2 \times 10^9 / [2 \text{ (N) (H) (Af)}] = 2.61$

MTTF = 10^9 / FIT = 43670 years

Chi² = Chi Squared Distribution, determined by the number of failures and confidence interval

N = Total Number of units from burn-in tests

H = Duration of burn-in testing

Af = Acceleration Factor from Test to Use Conditions (Ea = 0.7eV and T_{use} = 55°C)

Acceleration Factor [Af] = Exp [Ea / k (1/T, u - 1/T, s)]

Acceleration Factor ratio list:

	55 deg C	70 deg C	85 deg C	100 deg C	125 deg C	150 deg C	175 deg C
Af	758	256	95	38	9.7	2.9	1

T_J s = Stressed junction temperature in degree (Kelvin), K = C + 273.16

 $T_J u$ =The use junction temperature in degree (Kelvin), K = C + 273.16

k = Boltzmann's constant, 8.617164 X 10⁻⁵eV / K